## The Influence of Phosphonic Acid Protonation State on the Efficiency of Bis(diimine)copper(I)-based Dye Sensitized Solar Cells

## Alexander J. Stephens, Catherine E. Housecroft, Edwin C. Constable

University of Basel, Department of Inorganic Chemistry, CH-4506 Basel, Switzerland

E-mail: <u>alexander.stephens@unibas.ch</u>

The photoactive component of a Dye Sensitized Solar Cell (DSSC) consists of a dye molecule bound (either electrostatically or covalently) to a mesoporous TiO<sub>2</sub> surface through functional groups such as phosphonic acids.<sup>[1]</sup> Here, we investigate how the protonation state of such phosphonic acids affects their ability to anchor to TiO<sub>2</sub> substrates, and how the operational parameters of the resultant DSSCs are influenced in turn.

Stepwise titration of bases into a solution of  $LH_4$  alters the ligands protonation state and the nature of its associated cations to give  $[LH_n][X]_{n-4}$  (Fig. 1). The formation of  $Cu^I$  dye molecules is achieved by sequentially exposing TiO<sub>2</sub> electrodes to  $[LH_n][X]_{n-4}$ , followed by the homoleptic  $Cu^I$  complex of the ancillary ligand. Our results demonstrate that the addition of a small amount of base to  $LH_4$  (~1 eq) can afford up to a 30% increase in DSSC efficiency. These results are rationalized through consideration of proton / cation transfer from the ligand to the surface, deprotonation of surface hydroxides, and changes in the photochemical and electrochemical properties of ligand  $LH_4$  upon deprotonation.




Figure 1. The sequential formation of a bis(diimine)copper(I) dye on a TiO<sub>2</sub> electrode using phosphonic acids in different protonation states.

## **References:**

[1] C. E. Housecroft, E. C. Constable, *Chem. Soc. Rev.*, **2015**, 44, 8386.